



CERTIFICATE OF ANALYSIS

ORDER # : 257743
PART NUMBER: 242206357

CUSTOMER NAME: PACIFIC INDUSTRIAL SUPPLIES
UNIT 1/19 CHIPLEY STREET
SMITHFIELD NSW 2164
AUSTRALIA

CUSTOMERS ORDER NO: 40232
DIAMETER & LENGTH: 1/16
TRADE NAME: CORESHIELD
TYPE : 8
WEIGHT: 19,800
LOT NO: 81979
CLASSIFICATION : E71T-8
TEST KEY : 5857150000A

This material conforms to :
AWS A5.20-95

CHEMICAL ANALYSIS :

Carbon	.1998
Manganese	.4669
Chromium	.0325
Nickel	.0211
Silicon	.1369
Columbium	.0030
Tantalum	.0010
Molybdenum	.0090
Copper	.0531
Titanium	.0613
Phosphorus	.0046
Sulphur	.0037
Vanadium	.0092
Cobalt	.0029
Aluminium	.7020

(P=Predicted/W=Wet)

RADIOGRAPHY :

IRAY Satisfactory

TENSILE REQUIREMENTS:

AS WELDED

MIN YIELD(psi) :	58000
MIN YIELD(MPa) :	400
MIN TENSILE(psi) :	70000
MIN TENSILE(MPa) :	480
MIN ELONG :	22.0

MAX TENSILE(MPa) :

TENSILE RESULTS :

AS WELDED

CALCULATE YIELD(psi) :	68000
CALCULATE YIELD(Mpa) :	469
CALCULATE TENSILE(psi) :	78500

The ESAB Group, Inc.

1500 Karen Lane
Hanover, PA 17331
www.esab.com
Fax: 1-800-444-8911

By:

K. Wildasin
K. Wildasin, Supervisor, Q.A. Services





CERTIFICATE OF ANALYSIS

ORDER # : 257743
PART NUMBER: 242206357

CALCULATE TENSILE (Mpa) : 542
% ELONGATION : 25.0
% REDUCTION OF AREA : 57.5

CHARPY V-NOTCH REQUIREMENTS:AS-WELDED :

CVN TEMPERATURE (F) : -20
CVN TEMPERATURE (C) : -29
CVN AW MIN (FT-LBS) : 20
CVN AW MIN (JOULES) : 27

CHARPY V-NOTCH RESULTS:AS-WELDED :

TEMP (F)	FT-LBS	TEMP (C)	JOULES	GAS
-20	44	-29	60	

FILLET : Satisfactory

This material is certified to be free of any mercury.

The undersigned certifies that the product supplied will meet the requirements of the applicable AWS Filler Metal Specification when tested in accordance with that specification, and that no significant change has been made in the elements described in the qualification approval

The ESAB Group, Inc.

1500 Karen Lane
Hanover, PA 17331
www.esab.com

Fax: 1-800-444-8911
Phone: 1-800-423-5540

By:

K. Wildasin

K. Wildasin, Supervisor, Q.A. Services

